

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C08J 7/04, C09D 183/06 G02B 1/10	A1	(11) International Publication Number: WO 94/10230 (43) International Publication Date: 11 May 1994 (11.05.94)
(21) International Application Number: PCT/EP93/03102 (22) International Filing Date: 5 November 1993 (05.11.93) (30) Priority data: 07/972,359 5 November 1992 (05.11.92) US (71) Applicant: ESSLOR INTERNATIONAL [FR/FR]; Compagnie Générale d'Optique, 1, rue Thomas-Edison, F-94028 Créteil (FR). (72) Inventors: TARSHIANI, Yassin, Yusef ; 8073 Somerset Drive, Largo, FL 34643 (US). WEBER, Steven, Anthony; 8301 Riverside Drive, St. Petersburg, FL 33702 (US).		(74) Agent: BUREAU D:A. CASALONGA-JOSSE; Morassistrasse 8, D-80469 Munich (DE). (81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: EPOXYSILANE COATING COMPOSITIONS (57) Abstract <p>A radiation-curable coating composition for ophthalmic lens is disclosed which comprises a monoepoxysilane and an ultraviolet activated photoinitiator capable of initiating a cationic cure of such composition. The photoinitiator is an aromatic onium salt or an iron arene salt complex.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

Epoxysilane coating compositions.

This invention relates, generally, to a coating composition for forming an abrasion-resistant coating for solid substrates such as ophthalmic lens or other optical articles, and more particularly to a monoepoxysilane composition which is easily curable by radiation.

10 Synthetic plastic materials have come into wide use as a lightweight, safe material for ophthalmic lens instead of inorganic glass. However, most plastic materials scratch easily, and are susceptible to chemical attack, when compared to inorganic glass optical products.

15 Thus, protective coatings for plastic substrates which are abrasion resistant are in great demand and of great interest to the art.

The broad application of protective coatings to a lens substrate is known. Typically, these protective coatings are applied to the desired substrate by spin coating, dip coating, spray coating, and flow coating techniques. Vapor coating techniques are also well known, and to a limited extent, certain in-mold techniques have also been practiced.

20 Many of the prior art abrasion resistant coatings result from thermally activated initiators, which require exposure to elevated temperature in order to fully develop the physical properties of the coating. Unfortunately, these thermally cured coatings do not become tack-free immediately upon being subjected to the elevated temperatures needed for curing. The tack-free state is achieved after the passage of significant time, sometimes hours. This "lag-time" or delay in achieving a tack-free state presents an opportunity for the coating to be marred by various environmental factors, e.g., airborne particulate matter.

30 In response, the art has utilized radiation-curable

abrasion resistant coatings. The technique of radiation cure does result in a coating composition which is tack-free within seconds of irradiation. The current practice is to use radiation for the cure and utilize a free radical polymerization mechanism with various acrylate monomers to achieve the abrasion-resistant coating.

Radiation curable acrylate coatings have drawbacks. Since the acrylate coatings result from free radical polymerization, careful steps must be taken to exclude oxygen during the coating process. If not excluded, oxygen will inhibit the reaction and the coating will have an inferior surface hardness. An oxygen-free environment is expensive and cumbersome to achieve and maintain during the coating process.

It is therefore highly desirable to formulate a coating composition which is radiation-curable and is formulated in a normal environment including air or oxygen, i.e., expensive oxygen removal steps are avoided.

Abrasion resistant coatings resulting from cationic mechanisms are known. Unlike the free radical mechanisms, cationic polymerization is not inhibited by atmospheric oxygen. However, to achieve satisfactory results, some coatings achieved through cationic polymerization still require the acrylate base. Acrylates are notoriously toxic and tend to shrink. This relatively large shrinkage many times results in poor adhesion of the coating to the substrate, and expensive pretreatment of the substrate is required in order to improve the adhesion.

The present invention obtains excellent clarity and physical properties without the use of acrylate-functional silanes or multifunctional acrylate monomers. In the present invention, an abrasion resistant coating which is radiation curable is obtained from a monoepoxysilane by utilizing a cationic photoinitiator as the only required initiator.

In accordance with the present invention, a coating

composition for imparting abrasion and scratch resistance to solid substrates and in particular, a coating for imparting such resistance to ophthalmic lens.

5 It is an object of the present invention to provide a novel protective coating to solid substrates and other relatively smooth solid surfaces.

It is another object of the present invention to provide a novel coating composition which imparts abrasion and scratch resistance to ophthalmic lens.

10 A still further object of the present invention is to provide a radiation-curable coating composition which imparts abrasion and scratch resistance to solid substrates and other relatively smooth solid surfaces.

15 Still another object of the present invention is to provide a radiation-curable coating composition for ophthalmic lens.

Another object of this invention is to provide an ophthalmic lens coated with a radiation-curable coating composition which imparts abrasion and scratch resistance to the coated lens.

20 It is a feature of this invention to have a UV curable coating composition which rapidly yields a tack-free film which is further cured to a substantially non-tintable, abrasion resistant coating with excellent adhesion.

25 Other and further objects and features of the present invention will be apparent from the description that follows:

30 In general, the present invention contemplates a radiation-curable coating composition comprising a monoepoxysilane and an ultraviolet photoinitiator capable of initiating a cationic cure of such composition. The photoinitiator is a photosensitive aromatic onium salt or an iron arene salt complex. The preferred photoinitiator comprises an iron arene salt complex.

35 Preferentially, the radiation-curable coating composi-

tion of the invention further comprises colloidal silica.


The preferred radiation-curable coating compositions contains also an alkoxysilane crosslinking agent.

5 More particularly, the present invention provides a substantially non-tintable coating composition for an optical lens to render the lens resistant to abrasion comprising 5 to 25 parts by weight of a hydrolyzable monoepoxysilane, 2.5 to 7 parts by weight of an alkoxysilane crosslinking agent, 2.5 to 50 parts by weight of colloidal silica, 0.1 to 10 3 parts by weight of an ultraviolet activated photoinitiator sufficient to initiate a cationic cure of such composition, and 50 to 90 parts by weight of solvent.

Also, in general, the present invention contemplates ophthalmic lens coated with the novel composition of this 15 invention.

The present invention relates to a coating composition curable to a tack-free state upon irradiation with ultraviolet radiation comprising preferentially a monoepoxysilane having at least two alkoxy groups.


More particularly, the monoepoxysilane used according to the present invention corresponds to the formula:



wherein E is a group containing a glycidoxy group or an epoxycyclohexyl group, or a mixture of both; R¹ is an alkylene group containing from 1 to 4 carbon atoms; R² and R³ are alkyl groups containing from 1 to 4 carbon atoms; and a is an integer of 0 or 1; an aqueous, aqueous-alcoholic or alcoholic dispersion of colloidal silica; a crosslinking agent; and a photoinitiator for an ultraviolet activated cationic cure.

More specifically, the coating composition of the present invention comprises

(a) a hydrolyzable monofunctional monoepoxysilane consisting of a compound of the general formula



wherein E is a group containing a glycidoxy group or an epoxycyclohexyl group, or a mixture of both; R¹ is an alkylene group containing from 1 to 4 carbon atoms; R² and R³ are alkyl groups containing from 1 to 4 carbon atoms; and a is an integer of 0 or 1,

(b) an acidic dispersion of colloidal silica,

(c) an alkoxysilane crosslinking agent, and,

(d) an ultraviolet radiation activated photoinitiator.

The alkoxysilane crosslinking agent is of the general formula



wherein

10 R^7 is alkyl group containing from 1 to 2 carbon atoms

or,

is an alkoxy group containing 1 to 2 carbon atoms,

15 and,

R^8 is an alkyl group containing from 1 to 2 carbon atoms,


20 with the proviso: if R^7 is an alkoxy group, R^7 and OR^8 are identical.

In other aspects, the present invention provides a substantially non-tintable coating composition for ophthalmic lens to render the lens resistant to abrasion comprising:

25

(1) 5 to 25% by weight of a hydrolyzable monofunctional organoalkoxysilane selected from the group consisting of a compound of the general formula


30



35 wherein E is a group containing a glycidoxy group or an epoxycyclohexyl group, or a mixture of both; R^1 is an alky-

lene group containing from 1 to 4 carbon atoms; R^2 and R^3 are alkyl groups containing from 1 to 4 carbon atoms; and (a) is an integer of 0 or 1.

(2) 2.5 to 7% by weight of a crosslinking agent of the general formula



wherein

R^7 is an alkyl group or an alkoxy group containing from 1 to 2 carbon atoms,

and,

R^8 is an alkyl group containing from 1 to 2 carbon atoms with the proviso: if R^7 is alkoxy, R^7 and OR^8 are identical,

(3) 2.5 to 50% by weight of colloidal silica disposed in water, alcohol or alcohol-water mixtures,

(4) 0.1 to 3% by weight of an ultra-violet activated photoinitiator capable of initiating a cationic cure and which is a photosensitive aromatic onium salt or is an iron arene salt complex,

(5) 0.05 to 0.25% by weight of a surface active agent; and,

(6) 50 to 90% by weight solvent.

The monoepoxysilanes are commercially available and include, for example, monoepoxysilanes available from the Specialty Chemicals Division of Union Carbide Chemicals and Plastics Corporation known as A-186 beta - (3,4-epoxycyclohexyl)-ethyltrimethoxysilane, and A-187 (gamma-glycidoxypropyl-trimethoxysilane). Another organoalkoxysilane may be obtained from HULS America, Inc., i.e., (3-glycidoxypropyl)-methyl-

diethoxysilane. Another example is gamma-glycidoxypropyl-methyl-dimethoxy-silane. These commercially available mono-epoxysilanes are listed solely as examples, and are not meant to limit the broad scope of this invention.

5 Specific examples of the alkoxysilane crosslinking agent of the present invention include methyltrimethoxysilane, ethyltrimethoxysilane, butyltrimethoxysilane, phenyltrimethoxysilane, methyltriethoxysilane, ethyltriethoxysilane, phenyltriethoxysilane, tetramethoxysilane, tetraethoxysilane, 10 methyltriacetoxysilane, ethyltriacetoxysilane, isopropyltriacetoxysilane, phenyltriacetoxysilane, and ethyltripropionyloxysilane, aminomethyltriethoxysilane, aminoethylaminomethyltrimethoxysilane, aminopropyltriethoxysilane, gamma-mercaptopropyltrimethoxysilane, gamma-mercaptopropyl- 15 triethoxysilane, gamma-uredopropyltrisilane, ethylene bistrimethoxysilane, propylenebistrimethoxysilane, and ethylenebistriethoxysilane.

Colloidal silica as used in this invention may have a particle size of 1 nanometer to 1000 nanometers in diameter. 20 Preferred diameter is in the range of 4 to 100 nanometers, more specifically, 10 to 60 nanometers. The silica may be dispersed in or have crystal-like particles in an aqueous, or polar solvent or the combination of both compounds. Preferably, the silica particles are dispersed in acidified 25 water, methanol, isopropanol, ethanol, butanol, polyethylene, glycol or combinations thereof.

The pH of the coating composition liquid is maintained between 3 and 5 to prevent gelation. If necessary, the pH can be adjusted by using hydrochloric acid or sodium hydroxide. 30

The photoinitiators suitable for use in the coating composition of the present invention are those that induce a cationic cure when irradiated with ultraviolet radiation. Suitable photoinitiators are the photosensitive aromatic 35 onium salts which are described in U.S. patent numbers

3.981.897, 4.058.401, 4.138.255 and 4.161.471 the teachings of which are incorporated herein by reference thereto.

Examples of suitable photosensitive aromatic onium salts include triphenylselenonium, hexafluoroantimonate, triphenylsulfonium hexafluoroantimonate, triphenylsulfonium, hexafluorophosphate, and bis (4-dodecylphenyl) - iodonium hexafluoroantimonate. Other cationic photoinitiators may also be used in this invention. A preferred photoinitiator is that produced by the Additives Division of Ciba-Geigy Corp. under the tradename of Irgacure 261, also known as

(.ETA. 5-2,4-cyclopentadiene-1-yl) [(1, 2, 3, 4, 5, 6-.ETA)-(1-1-methylethyl) benzene] iron⁽¹⁺⁾ hexafluorophosphate⁽¹⁻⁾, and generally referred to herein as an iron arene salt complex. Coatings produced with onium salt photoinitiators tend to yellow after irradiation due to the continuing presence of the chromophore. The chromophore of the product Irgacure 261 is destroyed upon irradiation and initiation, resulting in no yellowing of the coating.

These cationic photoinitiators are particularly effective for initiating a cross-linking reaction upon exposure to ultraviolet radiation such as that provided by UV lamps. The light source of the UV lamp may be mercury arc lamps, middle pressure mercury lamps, high pressure mercury lamps, metal halide lamps and the like. Exposure time to ultraviolet light may range from 1 to 60 seconds, typically, 10 to 30 seconds of exposure is satisfactory.

When preparing a coating composition of the present invention, the total solids content of the composition should, preferably, be between 10% and 50% by weight, with one or a mixture of solvents comprising the remainder of the formulation. Solvents which are useful in the practice of this invention include low molecular weight alcohols or alcohol-water mixtures, such as methanol, butanol, isopropanol and mixtures thereof; ketones, esters, glycol ethers, cellosolve, organic halides, carboxylic acids, aromatic compounds, and

mixtures thereof.

The organoalkoxysilane is relatively easily hydrolyzed in water, or in an aqueous solution including hydrochloric acid, sulfuric acid, acetic acid, phosphoric acid, and the like. The hydrolysis may take place in the presence or absence of a solvent, and preferably, may take place utilizing the excess acidic water in the colloidal silica.

In the practice of the present invention, it may be desirable to add to the coating composition a surface active agent. The surfactant may be non-ionic or ionic. Suitable non-ionic surfactants include compounds from fluorochemicals, such as FC-430 manufactured by the 3M Company, fluorinated alkyl alkoxyates, fluorinated alkyl sulfoamide, fluorinated alkyl ester, monoglyceryl series, the sorbitan fatty acid ester series, the cane sugar ester series, the polyoxyethylene ethers of higher alcohol series, the polyoxyethylene esters of higher fatty acids series, the polyoxyethylene ethers of sorbitan esters series, the fatty acid alkanolamide series, the polypropylene and polyoxyethylene series and the like. Concentration of the surfactant should be greater than 0.01 weight percent and preferably between 0.01 weight percent and 5 weight percent. Other additives such as leveling agents, and viscosity modifiers may be included in the coating composition by simple mixing. Examples of useful leveling agents are silicon surfactants such as a copolymer of lower alkylene oxide and lower polydimethylsiloxane.

The transparent substrate preferably used in the present invention include acrylic resins, polycarbonates, diethylene glycol bisallyl carbonate polymers, (halogenated) bisphenol A di(meth) acrylate homopolymers and copolymers, and (halogenated) bisphenol A urethane-modified di(meth) acrylate homopolymers and copolymers and polyurethane. The substrate itself can be tinted, if desired, by means known to the art; although the coating composition of the present

invention is substantially non-tintable.

5 The thickness of the coating composition as applied to the substrate can be selected within a broad range to meet the predetermined purpose or objective; but, typically, the range of 0.5 to 10 microns thick coating, preferably between 2 to 5 microns, offer excellent abrasion resistance to a lens substrate coated therewith. The coating may be applied by conventional methods such as brushing, rolling, spraying, spinning, and dipping.

10 The physical properties tested in the examples given below are Bayer Abrasion resistance, steel wool scratch resistance, and cross-hatch adhesion.

15 Bayer Abrasion resistance is determined by measuring the percent haze of a coated and uncoated lens, before and after testing on an oscillating sand abrader as in ASTM # F 735-81. The abrader is oscillated for 300 cycles with approximately 500g of sand, retained by #8 and #14 size mesh, used. The haze is measured with a Pacific Scientific Hazemeter model XL-211. The ratio of the uncoated lens haze (final- initial) to the coated lens haze (final-initial) is 20 a measure of the performance of the coating, with a higher ratio signifying a higher abrasion resistance. The following schedule is used for reporting Bayer Abrasion values for the examples given below: A= ratio of 4.4 or higher; B= ratio of 25 3.0 to 4.4; C - ratio of 1.5 to 3.4; D = ratio of less than 1.5.

Steel wool scratch resistance was determined as follows: the lens was mounted coated surface up with double sided tape on the end of a one inch diameter pivoting rod. Steel 30 wool (000 grade) was then pressed against the coated surface with a five pound weight as back-pressure. The lens was then oscillated for 200 cycles against the steel wool (one inch travel), and the haze measured. The difference in haze (final-initial) as measured on a Pacific Scientific Hazemeter 35 model XL-211 is reported as the steel wool scratch resistance.

ce value according to the following schedule: A= 0 -0.15; B= 0.16 - 0.30; C= 0.31 - 0.50; D= greater than 0.50.

Coating adhesion was measured by cutting through the coating a series of 10 lines, spaced 1mm apart, with a razor, followed by a second series of 10 lines, spaced 1mm apart, at right angles to the first series, forming a crosshatch pattern. After blowing off the crosshatch pattern with an air stream to remove any dust formed during the scribing, clear cellophane tape was then applied over the crosshatch pattern, pressed down firmly, and then rapidly pulled away from coating in a direction perpendicular to the coating surface. Application and removal of fresh tape was then repeated two additional times. The lens was then subjected to tinting to determine the percentage adhesion, with tinted areas signifying coating adhesion failure.

The following examples are set forth for illustrative purposes and should not be construed as limiting the scope of this invention. In the following examples, parts refers to parts by weight.

EXAMPLE 1

Preparation of hydrolyzed beta-(3,4-epoxycyclohexyl) ethyl-trimethoxy-2-silane

With stirring, 219 parts of an aqueous solution of 0.10 HCl was slowly added to 1000 parts of beta-(3,4 epoxy-cyclohexyl)-ethyl-trimethoxysilane over the course of one hour. After the addition of the aqueous solution was complete, the resulting solution was stirred at room temperature for 24 hours.

A composition was prepared by mixing 52.70 parts hydrolyzed beta-(3,4-epoxycyclohexyl) ethyltrimethoxysilane with 10.41 parts methyltrimethoxysilane crosslinker, 15.74 parts

aqueous colloidal silica (1034-A; Nalco Chemical Co.), 0.27 parts of a fluorosurfactant, 59.37 parts acetone, and 59.37 parts methanol. Next was added 2.13 parts General Electric UV 9310C photoinitiator, and the resulting solution again
5 mixed. After filtering, the composition was applied to cured diallyl diglycol carbonate lenses which were then passed under two Fusion Systems "D" bulbs for an irradiation time of 30 seconds, whereupon the coating was dry, aberration free, and tackfree to the touch. The lenses were then post-
10 cured for 3 hours at 105°C. After cooling to room temperature, physical tests were performed, and are listed in Table 1.

15

EXAMPLE 2

Preparation of hydrolyzed gamma-glycidoxypropyltrimethoxysilane

20 With stirring, 228 parts of an aqueous solution of 0.10N HCl was slowly added to 1000 parts of gamma-glycidoxypropyltrimethoxy-silane over the course of one hour. After the addition of the aqueous solution was complete, the resulting solution was stirred at room temperature for 24
25 hours. A composition was prepared by mixing 25.34 parts hydrolyzed gamma-glycidoxypropyltrimethoxysilane with 15.36 parts methyltrimethoxy-silane crosslinker, 44.80 parts 1034-A colloidal silica, 0.13 parts of a fluorosurfactant, and 212.84 parts acetone. After mixing the resulting solution,
30 1.54 parts General Electric UV9310C photoinitiator was added, and the solution again mixed. After filtering, the composition was applied to cured diallyl diglycol carbonate lenses, which were then irradiated and postcured in a manner identical to that described in example 1. Physical testing
35 results are listed in Table 1.

TABLE 1

	Example	Bayer Abrasion	Steel Wool	Adhesion
5	1	D	B	100%
	2	C	B	100%
	3	C	A	100%
	4	B	B	100%
	5	B	B	100%
10	6	B	A	100%
	7	A	A	100%
	8	A	A	100%
	9	A	A	100%

15 Bayer values

A = > 4.4
 B = 3.0 - 4.4
 C = 1.5 - 2.9
 D = < 1.5

Steel Wool values

A = 0 - 0.15
 B = 0.16 - 0.30
 C = 0.31 - 0.50
 D = > 0.50

20

EXAMPLE 3

25 A composition was prepared by mixing 47.05 parts hydro-
 lyzed gamma-glycidoxypyrpyltrimethoxysilane with 14.68 parts
 methyltrimethoxy-silane crosslinker, 22.21 parts 1034-A col-
 loidal silica, 0.02 parts of a fluorosurfactant, and 213.60
 parts methanol. After the resulting solution was thoroughly
 30 mixed, 1.88 parts General Electric UV9130C photoinitiator
 was added, and the solution mixed and then filtered. The
 composition was then applied to cured diallyl diglycol car-
 bonate lenses, which were then irradiated and postcured in a
 manner identical to that described in example 1. Physical
 35 testing results are listed in Table 1.

EXAMPLE 4

5 A composition was prepared by mixing 29.78 parts hydro-
lyzed gamma-glycidoxypropyltrimethoxysilane with 13.54 parts
tetraethoxysilane crosslinker, 90.74 parts colloidal silica
in 40% isopropanol, 0.20 parts of an ionic surfactant, and
80.24 parts methanol. Next was added 1.50 parts Irgacure 261
(Ciba Geigy Corp.) photoinitiator, with the resulting solu-
10 tion being mixed again, followed by filtration. The com-
position was then applied to cured diallyl diglycol carbo-
nate lenses, which were then placed under a 375 watt infra-
red lamp (lamp distance, 1 1/2 inches) for 17 seconds, and
then irradiated in a manner identical to that described in
example 1. After UV irradiation, the coated lenses were
15 postcured for 1 1/2 minutes under a 375 watt infrared lamp
(lamp distance, 3 inches). Physical testing results are lis-
ted in Table 1.

20

EXAMPLE 5

25 A composition was prepared by mixing 30.66 parts hydro-
lyzed gamma-glycidoxypropyltrimethoxysilane with 11.68 parts
methyltrimethoxy-silane crosslinker, 94.02 parts colloidal
silica in 40% isopropanol, 0.14 parts of a fluorosurfactant,
0.14 parts of a non-ionic surfactant, and 61.60 parts metha-
nol. Next was added 1.76 parts Irgacure 261 (Ciba Geigy
Corp.) photoinitiator, with the resulting solution being
30 mixed again, followed by filtration. The composition was
then applied to cured diallyl diglycol carbonate lenses,
which were then placed under a 375 watt infrared lamp (lamp
distance, 1 1/2 inches) for 17 seconds, and then irradiated
and postcured in a manner identical to that described in
35 example 1. Physical testing results are listed in Table 1.

EXAMPLE 6

5 A composition was prepared by mixing 23.70 parts hydro-
lyzed gamma-glycidoxypropyltrimethoxysilane with 16.83 parts
methyltrimethoxy-silane crosslinker, 75.63 parts colloidal
silica in isopropanol (IPA-ST Nissan Chemical Co.), 0.18
parts of a fluorosurfactant, 0.18 parts of a non-ionic sur-
factant, and 171.90 parts methanol. After mixing the resul-
ting solution, 5.79 parts Irgacure 261 (Ciba- Geigy Corp.)
10 photoinitiator and 5.79 parts cumene hydroperoxide were ad-
ded, and the solution mixed and then filtered. The composi-
tion was then applied to cured diallyl diglycol carbonate
lenses, which were then passed under two Fusion Systems "D"
bulbs (200 watt bulbs) for a total irradiation time of 15
15 seconds, versus 30 seconds without the cumene hydroperoxide.
The lenses were then postcured for 3 hours at 105°C. After
cooling to room temperature, the lenses were subjected to
physical testing, with the results listed in Table 1.

20 EXAMPLE 7

A composition was prepared by mixing 16.41 parts hydro-
lyzed gamma-glycidoxypropyltrimethoxysilane with 11.65 parts
tetraethoxysilane, 52.60 parts colloidal silica in isopropa-
25 nol (IPA-ST; NISSAN CHEMICAL CO.), 0.38 parts of a fluoro-
surfactant, and 118.47 parts methanol. Next, 0.50 parts
Irgacure 261 photoinitiator (CIBA - GEIGY CORP.) was added,
and the resulting solution mixed and then filtered. The com-
position was then applied to cured diallyl diglycol carbona-
te lenses, which were then irradiated and postcured in a
30 manner identical to that described in Example 1. Physical
testing results are listed in Table 1.

EXAMPLE 8

A composition was prepared by mixing 30.06 parts hydrolyzed gamma-glycidoxypropyltrimethoxysilane, 21.28 parts tetraethoxysilane, 92.06 parts colloidal silica in 40% isopropanol /60% water mixture, 54.82 parts methanol, 0.12 parts of a fluorosurfactant, 0.12 parts of non-ionic surfactant, and 1.5 parts Irgacure 261 photo-initiator. The resulting solution was then thoroughly mixed and then filtered. The composition was then applied to cured diallyl diglycol carbonate lenses, which were then irradiated and postcured in a manner identical to that described in Example 1. Physical testing results are listed in Table 1.

EXAMPLE 9

A composition was prepared by mixing 44.37 parts hydrolyzed gamma-glycidoxypropyltrimethoxysilane, 20.28 parts tetraethoxysilane, 136.05 parts colloidal silica in 40% isopropanol /60% water, 96.33 parts methanol, 2.52 parts Irgacure 261 photoinitiator, 0.21 parts of a fluorosurfactant and 0.21 parts of a non-ionic surfactant. The resulting solution was thoroughly mixed and then filtered. The composition was then applied to cured diallyl diglycol carbonate lenses, which were then irradiated and postcured in a manner identical to that described in Example 1. Physical testing results are listed in Table 1.

This invention is clearly new and useful. Moreover, it was not obvious to those of ordinary skill in the art at the time it was made, in view of the prior art when considered as a whole.

It will thus be seen that the advantages of the present invention are efficiently attained and since certain changes may be made in the above construction without departing from the scope of the invention, it is intended that all matters contained in the foregoing description shall be interpreted


as illustrative and not in a limiting sense.

It is also to be understood that the following claims
are intended to cover all of the generic and specific
features of the invention herein described, and all state-
5 ments of the scope of the invention which, as a matter of
language, might be said to fall therebetween.

Now that the invention has been described,

CLAIMS

- 5 1. Radiation - curable coating composition comprising a monoepoxysilane and an ultraviolet activated photoinitiator capable of initiating a cationic cure of such composition.
- 10 2. Composition according to claim 1, wherein the photoinitiator is a photosensitive aromatic onium salt or an iron arene salt complex.
- 15 3. Composition according to claim 2, wherein the photoinitiator is an iron arene salt complex.
4. Composition according to claim 1, which further comprises colloidal silica.
- 20 5. Composition according to claim 1, which further comprises an alkoxysilane cross-linking agent.
6. Composition according to claim 1, wherein the monoepoxysilane contains at least two alkoxy groups.
- 25 7. Composition according to claim 6, wherein the monoepoxysilane is of the formula




35 wherein E is a group containing a glycidoxy₁ group or an epoxycyclohexyl group, or a mixture of both; R₁ is an alky-

lene group containing from 1 to 4 carbon atoms; R^2 and R^3 are alkyl groups containing from 1 to 4 carbon atoms; and a is an integer of 0 or 1.

- 5 8. Radiation curable composition comprising:
 (a) a hydrolyzable monoepoxysilane selected from the group consisting of a compound of the general formula

10



- 15 wherein E is a group containing a glycidoxy group or an epoxycyclohexyl group, or a mixture of both; R^1 is an alkylene group containing from 1 to 4 carbon atoms; R^2 and R^3 are alkyl groups containing from 1 to 4 carbon atoms; and a is an integer of 0 or 1.

20

- (b) an acidic dispersion of colloidal silica,
 (c) an alkoxysilane crosslinking agent, and
 25 (d) an ultraviolet activated photoinitiator initiating a cationic cure.

30

9. Composition according to claim 8, wherein the monoepoxysilane is gamma-glycidoxypropyltrimethoxysilane.


10. Composition according to claim 8, wherein the monoepoxysilane is beta-(3,4-epoxycyclohexyl)-ethyltrimethoxysilane.

35

11. Composition according to claim 8, wherein the photoini-

tiator is a photosensitive aromatic onium salt or an iron arene salt complex.

12. Composition according to claim 8, wherein the alkoxysilane crosslinking agent is of the general formula



10

wherein

- 15 R^7 is alkyl group containing from 1 to 2 carbon atoms,
or
an alkoxy group containing from 1 to 2 carbon atoms, and

20

R^8 is an alkyl group containing from 1 to 2 carbon atoms,

- 25 with the proviso: if R^7 is an alkoxy group, R^7 and OR^8 are identical.

13. Composition according to claim 12 wherein the alkoxysilane crosslinking agent is methyltrimethoxysilane.

- 30 14. Composition according to claim 12 wherein the alkoxysilane crosslinking agent is tetramethoxysilane.

15. Composition according to claim 12 wherein the photoinitiator is a triarylsulfonium salt, an alkylated diaryl iodonium salt or mixtures thereof.

35

16. Composition according to claim 12 wherein the photoinitiator is an iron arene salt complex.

5 17. A substantially non-tintable coating composition for ophthalmic lens to render the lens resistant to abrasion comprising from 10 to 50 weight percent solids, such solids comprising from 20 to 64 percent of hydrolyzed monoepoxysilane, from 15 to 40 percent alkoxysilane crosslinking agent,
10 and from 30 to 60 percent colloidal silica; with the remainder of such composition comprising solvent.

18. A substantially non-tintable coating composition for optical lens to render the lens resistant to abrasion comprising 5 to 25 parts by weight of a monoepoxysilane, 2.5 to 7 parts by weight of an alkoxysilane crosslinking agent, 2.5 to 50 parts by weight of colloidal silica, 0.1 to 3 parts by weight of an ultraviolet activated photoinitiator sufficient to initiate a cationic cure of such composition, and 50 to
20 90 parts by weight of solvent.

19. Ophthalmic lens coated with the composition according to claim 18.

25 20. Ophthalmic lens coated with the composition according to claim 1.

21. Ophthalmic lens coated with the composition according to claim 8.


30 22. Ophthalmic lens coated with the composition according to claim 17.

35 23. Ophthalmic lens coated with the composition according to claim 18.

24. A substantially non-tintable coating composition for ophthalmic lens to render the lens resistant to abrasion comprising:

- 5 (a) 5 to 25% by weight of a monoepoxysilane selected from the group consisting of a compound of the general formula

10




- 15 wherein E is a group containing a glycidoxy group or an epoxycyclohexyl group, or a mixture of both; R^1 is an alkylene group containing from 1 to 4 carbon atoms; R^2 and R^3 are alkyl groups containing from 1 to 4 carbon atoms, and (a) is an integer of 0 or 1.

20

- (b) 2.5 to 7% by weight of a crosslinking agent of the general formula

25



wherein

30

R^7 is an alkyl or alkoxy group containing from 1 to 2 carbon atoms, and

R^8 is an alkyl group containing from 1 to 2 carbon atoms

35

with the proviso: if R⁷ is alkoxy, R⁷ and OR⁸ are identical;

5 (c) 2.5 to 50% by weight of colloidal silica dispersed in water, alcohol, or alcohol-water mixtures;

10 (d) 0.1 to 3% by weight of an ultraviolet activated photoinitiator capable of initiating a cationic cure and which is a photosensitive aromatic onium salt or an iron arene salt complex;

(e) 0.01 to 0.25% by weight of a surface active agent; and,

15 (f) 50 to 90% by weight of solvent.

25. Composition according to claim 24, wherein the mono-epoxysilane is gamma-glycidoxypropyl-trimethoxysilane; the crosslinking agent is methyltrimethoxysilane; and the photoinitiator is a triaryl sulfonium salt, an alkylated diaryliodonium, or mixtures thereof.

26. Composition according to claim 24 wherein the mono-epoxysilane is gamma-glycidoxypropyltrimethoxysilane; the crosslinking agent is tetraethoxysilane; and, the photoinitiator is an iron arene salt complex.

27. Composition according to claim 24 wherein the monoepoxysilane is beta- (3,4-epoxycyclohexyl) ethyltrimethoxysilane; the crosslinking agent is methyltrimethoxysilane; and the photoinitiator is a triaryl sulfonium salt, an alkylated diaryliodonium salt, or mixtures thereof.

28. Composition according to claim 24 wherein the mono-epoxysilane is beta-(3,4-epoxycyclohexyl) ethyltrimethoxysilane; the crosslinking agent is tetraethoxysilane; and the

photoinitiator is an arene salt complex.

29. Ophthalmic lens coated with the composition according to claim 25.

5

30. Ophthalmic lens coated with the composition according to claim 26.

10

31. Ophthalmic lens coated with the composition according to claim 27.

32. Ophthalmic lens coated with the composition according to claim 28.

INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/EP 93/03102

A. CLASSIFICATION OF SUBJECT MATTER

IPC 5 C08J7/04 C09D183/06 G02B1/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C08J C09D G02B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,4 486 504 (CHUNG) 4 December 1984 see claim 1 ---	1,2, 4-15, 17-27, 29-31
X	DATABASE WPI Derwent Publications Ltd., London, GB; AN 86-109331 & JP,A,61 051 101 (TORAY) 13 March 1986 see abstract ---	1
A	EP,A,0 407 174 (SWEDLOW) 9 January 1991 see claim 1 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- * "A" document defining the general state of the art which is not considered to be of particular relevance
- * "E" earlier document but published on or after the international filing date
- * "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- * "O" document referring to an oral disclosure, use, exhibition or other means
- * "P" document published prior to the international filing date but later than the priority date claimed

* "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

* "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

* "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

* "&" document member of the same patent family

Date of the actual completion of the international search

15 February 1994

Date of mailing of the international search report

10. 03. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Lentz, J

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat Application No

PCT/EP 93/03102

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4486504	04-12-84	NONE	
EP-A-0407174	09-01-91	US-A- 5013608	07-05-91
		AU-B- 624050	28-05-92
		AU-A- 5873890	10-01-91
		CA-A- 2019694	07-01-91
		CN-A- 1049171	13-02-91
		JP-A- 3170569	24-07-91
		US-A- 5102695	07-04-92